

# Ferrite Tile Absorber



## Description

RF absorber is utilized to reduce reflections within an RF shielded enclosure

## Features

Standard size 600mm x 600mm panel with 36 tiles
5.5mm Thickness ( IEC-61000-4-3 )
6.3mm Thickness ( ANSI-C63.4 )

Ferrite tile absorbers provide an attractive alternative to large, foam-type absorber materials for new anechoic chambers or for upgrading older rooms for radiated emission and immunity measurements.

Ferrite tiles are used wherever high absorption ( -15 to -25 dB at < 100 MHz ) and compact size ( 6mm vs. 2400mm for foam absorbers ) are required.

Ferrite tiles are immune to fire, humidity and chemicals which provide a reliable and compact solution for attenuating plane wave reflections in shielded enclosures.

Standard attachment: panels are held in place with countersunk screws.



## Specification

